

# 試驗報告



報告編號：KV-20-10998

頁數：1 OF 1

報告日期：110年01月06日

委託單位：証旭事業有限公司

樣品名稱：隔音墊緩衝材 JS-ER-01 8mm

送驗人員：証旭事業有限公司(胡正輝)

收件日期：109年12月28日

試驗日期：109年12月28日~110年01月06日

- 備註：
- 1.以上資料由顧客提供(收件及試驗日期除外)
  - 2.除非另有說明，此報告結果僅對測試之樣品負責  
未經本公司事先書面同意，此報告不可部分複製
  - 3.下述報告內容標示#處由顧客提供

## 試驗結果：

試驗項目	試驗方法	試驗結果
3000kgf/m <sup>2</sup> 時抗壓減厚(mm)	萬能試驗機(註.1)	0.549
硬度(Type A/1 sec)	ASTM D2240-15 <sup>e1</sup>	36

註：#1.試驗試片及 3000kgf/m<sup>2</sup>時抗壓減厚試驗方法，

取試驗樣品尺寸 50\*50mm 施以初始應力使承壓塊密合試驗試片表面，

應力：1：0.223 kgf/cm<sup>2</sup>，

2：0.211 kgf/cm<sup>2</sup>，


3：0.222 kgf/cm<sup>2</sup>，

將應力歸零，再壓至 3000kgf/m<sup>2</sup> 並記錄其厚度減少量(mm)。

2.本試驗報告之試驗地點同實驗室地址。

----- oOo -----

本報告若有提供規範值，該規範值僅供參考，合格之判定以委託單位實際要求為準

  
 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.